

## **Boral Construction Materials Materials Technical Services**

Unit 4, 3-5 Gibbon Road Baulkham Hills NSW 2153 Australia PO Box 400, Winston Hills NSW 2153

T: +61 (02) 9624 9900 F: +61 (02) 9624 9999

www.boral.com.au

## NOTIFICATION OF N.A.T.A TEST REPORT REPLACEMENT

CLIENT: VICTORIAN CHEMICAL CO. PTY LTD

FILE NO: 828/16

PROJECT: Properties Testing of Aggrebond PC Adhesion Agent using 14mm Sealing

Aggregate from Mt. Bundey Quarry

REPORT NO. OF REPORT BEING REPLACED: 151964 & 152041

**NEW REPORT NO:** 

154454

REASON FOR REPLACEMENT: Client requested product identification to be updated

SIGNATURE: NAM)

DATE: 3/3/17

Report Template - Revision 1. April 2014 - Authorised by K. Ali Page 1 of 1



## **Boral Construction Materials Materials Technical Services**

Unit 4, 3-5 Gibbon Road Baulkham Hills NSW 2153 Australia PO Box 400, Winston Hills NSW 2153

T: +61 (02) 9624 9900 F: +61 (02) 9624 9999

www.boral.com.au

## **TEST REPORT**

CLIENT: VICTORIAN CHEMICAL CO. PTY LTD

FILE NO: 828/16

PROJECT: Properties Testing of Aggrebond PC Adhesion Agent using 14mm Sealing Aggregate from Mt. Bundey Quarry

TEST METHOD: AS1141 - Methods for Sampling and Testing Aggregates

REQUEST NO: 70143

Sample Description:		14mm Sealing Aggregate	
Location:		Mt. Bundey Quarry	
Laboratory Sample No:		184440	
Date Sampled:		26.9.16	
Date Received:		3.11.16	
Test Method	Test	As Received	Saturated Surface Dry
			Results
AS1141.50	Resistance to stripping of cover aggregates and binders  1. Binder: S10E + 1% Aggrebond PC Aggregate: As received, Precoated as per client's instructions. (%Stripped) Particle crumbled: Nil Softening point of binder: 72°C Oven temp. for 24 hrs conditioning: 92°C	2	2
	2. Binder: S25E + 1% Aggrebond PC Aggregate: As received, Precoated as per client's instructions. (%Stripped) Particle crumbled: Nil Softening point of binder: 78°C Oven temp. for 24 hrs conditioning: 98°C	6	10

Note: Replacement for Report No: 151964 & 152041
Sample submitted by Boral Staff Mt. Bundey Quarry
Aggrebond PC sampled by client at Victorian Chemicals

Precoat is 49.5% C170 ex SAMI + 49.5% Kerosene +1% Aggrebond PC.

Binders: S10E & S25E ex Fulton Hogan - Darwin

Adhesion Agent: Aggrebond PC

C. Leckie, File

NATA

ACCREDITED FOR
TECHNICAL
COMPETENCE

Donovan Lotts

Approved Signatory\_

Serial No.

154454