



PAVEMATE

Asphalt Mix Additive

Product Description

Pavemate is surfactant type additive for both hot and warm mix asphalt. The product is a liquid blend of fatty acid derivatives, with a unique formulation that includes antistripping properties. Pavemate is an ideal compaction aid, offering economic, operational and environmental benefits while delivering improved asphalt performance.

Attributes

- ❖ Enables lower compaction temperatures during asphalt paving operations
- ❖ Enables lower temperatures during asphalt manufacture
- ❖ Improves resistance to stripping
- ❖ Can reduce air voids in asphalt

Key Benefits

- ❖ Approved by Vic. DTP for use in PMB mixes.
- ❖ Supported by technical reports and laboratory results based on C450 and A10E
- ❖ Can expand market reach by allowing longer haulage distances
- ❖ Can extend paving season into cooler months
- ❖ Can lengthen workable hours in the day
- ❖ Improved workability
- ❖ Can help lower energy consumption at the point of asphalt manufacture
- ❖ Can result in reduced odours at the plant
- ❖ Improved work conditions
- ❖ Can assist in reducing greenhouse gas emissions
- ❖ Australian owned and made supporting Australian manufacturing



PAVEMATE †

Asphalt Mix Additive

Chemico-Physical Properties

Description	Oleyl Imidazoline
Appearance (20°C)	Oily liquid
Solids by weight (%)	100
Water (%)	< 1
Specific Gravity (20°C)	0.97
Odour	Amine
Amine Value (KOH/g)	700
Pour Point (0°C)	< 5
Flash Point (0°C)	> 150
Viscosity (cSt @ 20°C)	~125

Suggestions for Use

It is recommended that Pavemate be incorporated into the binder at the asphalt plant immediately prior to mixing with the aggregate.

At 0.3% w/w of the binder, Pavemate provides an equivalent compaction temperature above 110°C compared to a standard compaction of 150°C with TfNSW C450 AC 14 asphalt mix[#].

At 0.5% w/w of the binder, Pavemate provides an equivalent compaction temperature of about 140°C when compared to a standard compaction of 160°C with VIC DTP AE10 AC 14 VP asphalt mix[#].

Storage & Handling

Corrosive product - Wear protective gloves and safety goggles. See Safety Data Sheet for further information

Pavemate may be stored up to 12 months when kept in sealed containers between 4° and 50°C. Avoid freezing or prolonged storage at high temperature.

Avoid exposure to air for prolonged periods as a film or crust may form on the product Surface

Packaging

20L, 200L, 1000L, Bulk

Other Asphalt Products

Aggrebond PC – 100% active bitumen adhesion agent. (NSW, ACT, VIC, TAS, SA, WA, NT)

Aggrebond SS – 40% active bitumen adhesion agent. (NSW, ACT, VIC, TAS)

Aggrebond Platinum[†] – 100% active bitumen adhesion agent. (Qld)

SLIPWAY[†] Heavy Duty Slip agent for bitumen trucks

SLIPWAY[†] Light General purpose truck slip emulsion / Rubber roller anti-stick agent

DISPERSOL LITE A[†] - Heavy duty industrial cleaner for wax, bitumen & grease.

[†] Trademark used under license

[#] Detailed technical report available on request

The Company

The Company has unrelenting commitment to; integrity in relationships, the health and safety of people, care for the environment, innovation, development and continuous improvement, which is the foundation of its quality system ISO 9001:2015



83 Maffra Street, Coolaroo,
Victoria 3048, Australia
Telephone: (03) 9301 7000
Website; www.vicchem.com
Email: products@vicchem.com

Disclaimer: Victorian Chemical Company Pty. Ltd. has taken all reasonable care in preparing information contained in the bulletin. However, because the use of this information is beyond our control, Victorian Chemical Company Pty. Ltd. accepts no responsibility for any consequences whatsoever arising from the use of this information except responsibility imposed under any applicable law